

APCOFLOR SL 4

Three Components, 4 mm Self Leveling, Monolithic Epoxy Flooring

Product Description

- Self leveling coatings with excellent flow and leveling characteristics.
- Provides a hygienic and dust free environment.
- Hard wearing and chemically resistant.
- Attractive, easy to clean and maintain.
- Heavy duty ramps flooring and vehicle parking.

Designed Use

- Seamless flooring for showrooms, business centers, malls
- Clean coating to kitchen and poultrys,
- Pharmaceutical units, food processing plants, chemical plants and car parks.

Physical Data	Volume Solids (Based on ASTM D2697)	100 %
	Typical Dry Film Thickness	3 – 4 mm
	Wet Film Thickness	3 – 4 mm
	Theoretical Coverage	0.19 m ² /kg @ 3 mm dft
		0.14 m ² /kg @ 4 mm dft
	Colour	Range
Finish	Glossy	

Application Details - Method Of Application

- The product may be applied by a serrated/smooth trowel to the required thickness.
- The mixed material should be poured onto the primed surface and spread slowly and evenly.
- Ensure proper leveling and appearance, avoid overspreading.
- The material should be rolled firmly with a spike Roller to ensure compactness and de-aeration of the film.
- Avoid Roller marks prevent over rolling of the coating.
- Coverage would vary significantly based on the nature of the concrete surface.

Drying Time				
Ambient Temperature	Touch Dry	Hard Dry	Full Cure	Pot Life
25°C	4 hours	30 hours	7 days	60 minutes
35°C	3 hours	18 hours	5 days	30 minutes
45°C	2 hours	16 hours	3 days	15 minutes
No. of Components		Three		
Mixing Ratio (Aggregates - Base : Hardener)		25 : 62.5 : 12.5 (By weight)		
Application Conditions		Do not apply this product if the relative humidity exceeds 85%.		

Additional Information	Thinner/Cleaning solvent	Solvalux 7-45
	Storage Instruction	Store in a cool shaded dry area
	Flash Point	Mixed less than 28°C
	Packaging	10 Kg and 20 Kg
	Shelf Life	12 months

Surface Preparation

- A sound, clean and dry substrate is absolutely essential for successful coating application and in ensuring maximum bonding between the substrate and coating system. New concrete surface must be a minimum of 28 days old, free from curing compounds and sealers and have a moisture content less than 5% prior to application of the primer.
- The surface can be prepared mechanically using sand blasting, shot blasting or scarifier. Surface preparation by acid etching with hydrochloric acid followed by thorough water wash and wire brushing should be the last option where methods mentioned earlier can not be applied. Acid etching should be carried out in compliance to the local health and hazard regulations and should be necessarily supervised by skilled person. The choice of surface preparation should be determined by the extent and nature of contamination present on the concrete surface. All dust present must be removed by vacuum pump.
- After applying Apcoflor HFP 120 primer or SF Primer, all cracks present, based on the depth of the crack, should be filled either by epoxy, putty or mortar. Expansion joints should be brought up through the coating.

Mixing

- A suitable power driven mixer/stirrer is recommended for uniform mixing of the self leveling coating. Stir the base and hardener separately. Blend the aggregates in the base. Mix hardener gradually into the base under continuous stirring as per stated mixing ratio. Continue the mixing for 3 – 4 minutes. Mix the aggregates into the mixed resin portion uniformly under continuous mechanical agitation. Mix well for 5 – 6 minutes till the components become homogeneous. Apply before expiration of pot life.

Product Use Restrictions

- Generally recommended for interior use.
- Application method and higher drying temperature may affect the colour of the coating.
- As common with all epoxy products, this product also will tend to discolour and chalk on exposure to direct sunlight.
- Not suitable for rising damp.

Safety Precautions

- Avoid contact with skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust masks and gloves. Use a barrier cream.
- Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapour or spray.
- This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge. In case of fire – blanket flames with foam, carbon dioxide or dry chemicals
- Refer to MSDS for further information.

First Aid

- Eyes: In the event of accidental splashes, flush eyes with water immediately and obtain medical advice.
- Skin: Wash skin thoroughly with soap and water or approved industrial cleaner.
- Do not use solvent or thinners.
- Inhalation: Remove to fresh air, loosen collar and keep patient rested.
- Ingestion: In case of accidental ingestion, do not induce vomiting. Obtain immediate medical attention

Disclaimer

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.

“This Technical Data Sheet supersedes those previously issued with immediate effect

For more information please contact us at: “bahrain@bergeronline.com”

Berger Paints Bahrain W.L.L

Tel: +973-1712-3700

Fax: +973-1773-0689